







LL55 EXCELLENCE LOOSE-LAY LVT










TECHNICAL DATA SHEET

PHYSICAL PROPERTIES & PACKAGING (LOOSE-LAY 5.0 MM/0.55 MM)		
Collection	EXCELLENCE PLANK	EXCELLENCE TILE - XL
Use	Commercial & Residential	Commercial & Residential
Size	228.6mm x 1219.2mm (9" x 48")	457.2mm x 914.4mm (18" x 36")
Wear Layer - Thickness	0.55mm	0.55mm
Thickness - Overall	5.0mm	5.0mm
Edge Detail	4 sides Micro Bevel	4 sides Micro Bevel
Finish	Duraspect™ Extreme Surface Protectant	Duraspect™ Extreme Surface Protectant
Embossing(s)	Textured Concrete	Stoneline
Mass per Unit Area	9740 g/m ²	9740 g/m ²
Pieces/Carton	7 Pieces	5 Pieces
Coverage/Carton	1.95m ²	2.09m ²
Coverage/Pallet	40 Cartons (78.00m ²)	50 Cartons (104.52m ²)
Coverage/Container	24 Pallets (1872 m ²)	19 Pallets (1986 m ²)
Warranty ⁽¹⁾	Material: 20 years (100%) Labour: 10 years (Pro rata)	Material: 20 years (100%) Labour: 10 years (Pro rata)

EUROPEAN / INTERNATIONAL STANDARDS - MANUFACTURING & USAGE				
Description	Standard	Symbol	Requirements	Results
CE Certification	EN 14041		Refer to Standards Below	Refer to Results Below
Reaction to Fire (and Smoke Production)	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2		Bfl - s1 Classification Critical Flux: ≥8.0kW/m ² Flame Spread: ≤150mm within 20s Smoke Value as % x min: ≤750	Passes Requirements
Content of PCP (Pentachlorophenol)	EN 14041		<0.1ppm	Passes Requirements
Formaldehyde Emission	EN 717-1		Class E1: Release ≤0.124mg/m ³	Passes Requirements
Slip Resistance (Dry)	EN 13893		Class DS: Coefficient of Friction ≥0.3	Passes Requirements
Thermal Resistance	EN 12667		N/A	0.01745 m ² K/W at 10°C (tile) 0.0145 m ² K/W at 10°C (plank)






LL55 EXCELLENCE LOOSE-LAY LVT

TECHNICAL DATA SHEET

EUROPEAN / INTERNATIONAL STANDARDS - CE CERTIFICATION / TESTING				
Description	Standard	Symbol	Requirements	Results
Classification (Level of Use)	EN ISO 10582 EN ISO 10874		Commercial - Heavy (Class 42) Wear Layer (Nominal): $\geq 0.55\text{mm}$ Thickness (Nominal): $\geq 2.0\text{mm}$	Passes Requirements
Size, Squareness, and Straightness	EN ISO 24342		Size: $\leq 0.15\%$ from Nominal Squareness/Straightness: If Size $> 400\text{mm}$: $\leq 0.35\text{mm}$ If Size $\leq 400\text{mm}$: $\leq 0.25\text{mm}$	Passes Requirements
Thickness	EN ISO 24346		Average (from Nominal): $+0.13\text{mm} / -0.10\text{mm}$ Any Sample (from Average): $\pm 0.15\text{mm}$	Passes Requirements
Mass per Unit Area	EN ISO 23997		9571g/m^2	Passes Requirements
Dimensional Stability	EN ISO 23999		$\leq 0.25\%$	Passes Requirements
Curling	EN ISO 23999	N/A	$\leq 2\text{mm}$	Passes Requirements
Flexibility	EN ISO 24344 (Method A)		No Cracks (20mm Mandrel)	Passes Requirements
Residual Indentation	EN ISO 24343-1		$\leq 0.1\text{mm}$	Passes Requirements
Castor Chair	ISO 4918		After 25,000 Cycles: Delamination - None Appearance \leq "Slight Change"	Passes Requirements
Colour Fastness to Light	ISO 105-B02, Method 3		\geq Grade 6	Passes Requirements

LL55 EXCELLENCE LOOSE-LAY LVT

TECHNICAL DATA SHEET

EUROPEAN / INTERNATIONAL STANDARDS - AUXILIARY PERFORMANCE & SAFETY				
Description	Standard	Symbol	Requirements	Results
Slip Resistance (Wet)	DIN 51130	N/A	Grade R10: $\geq 10^\circ$ and $< 19^\circ$	Passes Requirements
Slip Resistance (Australia / New Zealand)	AS 4586	N/A	Wet Pendulum (Slider 96) P3: 35-44 SRV Oil-Wet Inclining Platform Grade R10: $\geq 10^\circ$ and $< 19^\circ$	Passes Requirements
Chemical Resistance	EN ISO 26987 / EN 423		N/A	No Effect
Abrasion / Wear Resistance	EN 660-2		N/A	Fv $\leq 2.0\text{mm}^3/100\text{r}$
Static Electrical Propensity	EN 1815, Method A		N/A	Average: $< 2\text{kV}$
Impact Sound Insulation ⁽²⁾	EN ISO 10140-3 ISO 717-2 EN ISO 140-8		N/A	$\Delta\text{LW} = 11\text{dB}$
A-weighted walking sound pressure level	EN 16205:2013		N/A	$L_{n,\text{walk}, A} = 82\text{ dB(A)}$

Footnotes

1) Warranty: Please see full terms and conditions of our warranties at www.aspecta flooring.com

2) Impact Sound Insulation (EN ISO 10140-3, ISO 717-2, EN ISO 140-8): ΔL_w = Weighted Reduction of Impact Sound Pressure Level

The manufacturing facility is ISO 9001 (Quality Management System) and ISO 14001 (Environmental Management System) certified.

Disclaimer: This document represents the current state of knowledge at the time of its publication and instantly supersedes all previous editions. It may be replaced, supplemented or amended at any time and without special notice. Please be sure to check the validity, relevance and content for topicality before issuing a guarantee claim at www.aspecta flooring.com



Just.

Declare.

