






| DESCRIPTION  |                 |                          |   |
|--|-----------------|--------------------------|---|
| Total thickness  | EN ISO 24346    | mm                       | 2.00  |
| Weight   | EN ISO 23997    | g/sqm                    | 3100  |
| Width of sheet   | EN ISO 24341    | cm                       | 200   |
| Length of sheet  | EN ISO 24341    | lm                       | 20  |
| CLASSIFICATION   |                 |                          |   |
| Standard / Product specification   |                 | -                        | EN ISO 10581  |
| European classification  | EN ISO 10874    | class                    | 34 - 43   |
| Fire rating  | EN 13501-1      | class                    | Bfl-s1  |
| Impact sound insulation  | EN ISO 717-2    | dB                       | 5   |
| Electrical resistance (1)  | EN 1081         | Ohm                      | $10^6 \leq R_t \leq 10^8$   |
| Static electrical propensity   | EN 1815         | kV                       | < 2   |
| Slip resistance  | DIN 51130       | Class                    | R9  |
| PERFORMANCE  |                 |                          |   |
| Type Binder content  | EN ISO 10581    | type                     | II  |
| Dimensional stability  | EN ISO 23999    | %                        | $\leq 0.40$   |
| Residual indentation (norm)  | EN ISO 24343-1  | mm                       | $\leq 0.10$   |
| Residual indentation (average measured value)                                      | -               | mm                       | $\sim 0.02$   |
| Castor chair test (type W)   | ISO 4918        | -                        | OK  |
| Thermal conductivity   | EN ISO 10456    | W/(m.K)                  | 0.25  |
| Colour fastness  | EN 20 105 - B02 | degree                   | $\geq 7$  |
| Surface treatment  | -               | -                        | Evercare™   |
| Chemical products resistance   | EN ISO 26987    | -                        | OK  |
| Anti viral activity (human coronavirus 229E)                                       | ISO 21702       |                          | 99.7% after 2h  |
| ENVIRONMENT / INDOOR AIR QUALITY   |                 |                          |   |
| TVOC after 28 days   | ISO 16000-6     | $\mu\text{g}/\text{m}^3$ | < 10  |
| Certification  | -               | -                        | Floorscore®   |
| MARQUAGE CE  |                 |                          |   |
|  | EN 14041        | -                        |    |
|  |                 | -                        |    |

(1) Measured before installation